

Greenfix Rootbarrier 400 Root Barrier

Greenfix Rootbarrier 400 consists of a woven HDPE (High Density Polyethylene) Base material which is reinforced and coated with a triple layer film of LDPE (Low Density Polyethylene). Available in green as standard and blue, orange and white to order. The Membrane is UV stabilised and suitable for outdoor applications.

Available in 205cm x 200m and 102.5cm x 100m rolls or client specific sized pre-welded panels



ITEM	VALUES	TEST METHODS
Weight	240 [g/m ²]	UNI EN 1849-2
Thickness	0,4 [mm]	UNI EN 1849-2
Tensile strength MD	21,22 [kN/m]	UNI EN ISO 1421
Tensile strength CMD	20,00 [kN/m]	UNI EN ISO 1421
Elongation at maximum load MD	18,0 [%]	UNI EN ISO 1421
Elongation at maximum load CMD	18,1 [%]	UNI EN ISO 1421
Static puncture resistance	2,72 [kN]	UNI EN ISO 12236
Shear strength of joints	553 [N]	UNI EN ISO 12317-2
Temperature resistance (Range)	- 30°C + 70°C	-
UV resistance (Grade)	360 kLy	DIN 54004
Liquid Permeability	< 10 ⁻⁶ [m ³ ·m ⁻² ·d ⁻¹]	UNI EN 14150
Methane Gas Permeability	1.41E-03 [m ³ m ⁻² .day.atm]	ASTM D 1434, Method V
Carbon Dioxide Gas Permeability	6.67E-03 [m ³ m ⁻² .day.atm]	ASTM D 1434, Method V
Moisture Permeability	1,32 · 10 ⁻¹⁴ [m s ⁻¹]	UNI EN 1931
Resistance to weathering	Variation of tensile strength and tensile elongation <25%	UNI EN 12224
Resistance to oxidation	Variation of tensile strength and tensile elongation <25%	UNI EN 14575

The specification presented above is to the best of our knowledge, true and accurate. Greenfix Soil Stabilisation and Erosion Control Limited (GSSEC) reserve the right to change any specification without prior notice. GSSEC cannot guarantee or offer warranty on products, unless agreed to in writing for specific conditions or for performance as the manner of handling, use and installation are beyond our control. We will not be liable for damages or losses, direct or indirect, of our GSSEC Range of Products due to the above reasons. All comparative data was correct at time of print. E&OE.